

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 398 363 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

17.03.2004 Bulletin 2004/12

(51) Int Cl.7: **C09K 11/06, H05B 33/14,
H01L 51/30**

(21) Application number: **03019525.9**

(22) Date of filing: **29.08.2003**

(84) Designated Contracting States:

**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT RO SE SI SK TR**

Designated Extension States:

AL LT LV MK

(72) Inventors:

- **Igarashi, Tatsuya**
Minami-Ashigara-shi Kanagawa (JP)
- **Watanabe, Kohsuke**
Minami-Ashigara-shi Kanagawa (JP)

(30) Priority: **29.08.2002 JP 2002251871**

(74) Representative: **HOFFMANN - EITLE**
Patent- und Rechtsanwälte
Arabellastrasse 4
81925 München (DE)

(71) Applicant: **Fuji Photo Film Co., Ltd.**
Kanagawa (JP)

(54) **Light emitting element and iridium complex**

(57) An organic electroluminescent element comprising: a pair of electrodes; and at least one organic layer provided between the pair of electrodes, at least one of the at least one organic layer being a light emitting layer, wherein the light emitting layer comprises at least one

transition metal complex represented by the formula (1), (2), (3), (4) or (5) as defined herein or an iridium complex represented by the formula (A), (6), (7) or (8) as defined herein.

EP 1 398 363 A1

Description

FIELD OF THE INVENTION

[0001] The present invention relates a light emitting element capable of converting an electric energy into a light to cause light emission. Also, the invention relates to a novel iridium complex that can suitably be used in the light emitting element. Especially, the light emitting element of the invention can suitably be utilized in organic electroluminescent (EL) elements.

BACKGROUND OF THE INVENTION

[0002] At present, research and development of various display elements are active. Especially, organic electroluminescent (EL) elements can obtain light emission with a high luminance at a low voltage, and therefore, are noticed as a promising display element.

[0003] As measures for enhancing characteristics of light emitting elements, there is reported a green light emitting element utilizing light emission from an ortho-metalated iridium complex (Ir(ppy)₃:Tris-Ortho-Metalated Complex of Iridium(III) with 2-Phenylpyridine) (see *Applied Physics Letters*, 75, 4 (1999)). This element attains an external quantum yield of 8 %, which is superior to an external quantum yield of 5 % that has hitherto been considered to be a limit in conventional elements. However, since this element is still low in efficiency and is limited to green light emission, it is narrow with respect to the range of application as a display. Thus, development of light emitting elements of other colors with a high efficiency has been demanded.

[0004] Complexes having a picolinic acid ligand and light emitting elements containing the same are disclosed (for example, see WO 01/41512, WO 02/44189 and WO 02/45466). However, light emitting elements containing a complex that can be driven at a lower voltage and can undergo light emission with a high luminance are demanded.

SUMMARY OF THE INVENTION


[0005] An object of the invention is to provide a light emitting element that can undergo light emission with a high luminance in a high efficiency and emits a light to multiple colors (especially brown to red colors).

[0006] Another object of the invention is to provide a transition metal complex that is used in the multicolor light emitting element.

[0007] The foregoing objects of the invention are attained by light emitting elements having the following constructions and transition metal complexes.


1. A light emitting element comprising at least one light emitting layer-containing organic layer between a pair of electrodes, the light emitting layer containing at least one transition metal complex represented by the following formula (1).

Formula (1)




In the formula (1), Q¹¹ represents a group of forming a nitrogen-containing condensed aromatic ring; Y¹¹ represents a connecting group (linking group); M¹¹ represents a transition metal ion; L¹¹ represents a ligand; X¹¹ represents a counter ion; Y¹¹ cannot be bonded to Q¹¹ to form an 8-hydroxyquinolinol ligand; n¹¹ represents an integer of from 0 to 4; m¹¹ represents an integer of from 1 to 4; q¹¹ represents an integer of from 0 to 3; and r¹¹ represents an integer of from 0 to 3.

2. The light emitting element according to the foregoing item 1, wherein the transition metal complex represented by the formula (1) is a transition metal complex represented by the following formula (2).

Formula (2)


In the formula (2), Q^{21} represents a group of forming a nitrogen-containing condensed aromatic ring; M^{21} represents a transition metal ion; L^{21} represents a ligand; n^{21} represents an integer of from 0 to 4; and m^{21} represents an integer of from 1 to 4.

3. The light emitting element according to the foregoing item 2, wherein the transition metal complex represented by the formula (2) is an iridium complex represented by the following formula (3).

Formula (3)


In the formula (3), R^{31} , R^{32} , R^{33} , R^{34} , R^{35} , and R^{36} each independently represents a hydrogen atom or a substituent, and adjacent groups thereof may be bonded to each other to form a condensed ring structure; L^{31} represents a ligand; n^{31} represents an integer of from 0 to 4; and m^{31} represents an integer of from 1 to 3.

4. The light emitting element according to the foregoing item 2, wherein the transition metal complex represented by the formula (2) is an iridium complex represented by the following formula (4).

Formula (4)


In the formula (4), R^{41} , R^{42} , R^{43} , R^{44} , R^{45} , and R^{46} each independently represents a hydrogen atom or a substituent, and adjacent groups thereof may be bonded to each other to form a condensed ring structure; L^{41} represents a ligand; m^{41} represents an integer of from 1 to 3; and n^{41} represents an integer of from 0 to 4.

5. The light emitting element according to the foregoing item 2, wherein the transition metal complex represented by the formula (2) is an iridium complex represented by the following formula (5).

Formula (5)


[0008] In the formula (5), R^{51} , R^{52} , R^{53} , R^{54} , R^{55} , and R^{56} each independently represents a hydrogen atom or a substituent, and adjacent groups thereof may be bonded to each other to form a condensed ring structure; L^{51} represents a ligand; m^{51} represents an integer of from 1 to 3; and n^{51} represents an integer of from 0 to 4.

6. An iridium complex represented by the following formula (A).

Formula (A)

In the formula (A), wherein A^1 , A^2 , A^3 , and A^4 each independently represents a hydrogen atom or a substituent, and adjacent groups thereof may be bonded to each other to form a benzene ring; A^5 and A^6 each independently represents a substituent; and t^{61} and t^{62} each independently represents an integer of from 0 to 4.


7. An iridium complex represented by the following formula (6).

Formula (6)

In the formula (6), R^{61} , R^{62} , R^{63} , R^{64} , R^{65} , and R^{66} each independently represents a hydrogen atom or a substituent; R^{67} and R^{68} each independently represents a substituent; and t^{61} and t^{62} each independently represents an integer of from 0 to 4.

8. An iridium complex represented by the following formula (7).


Formula (7)



In the formula (7), R^{71} , R^{72} , R^{73} , R^{74} , R^{75} , and R^{76} each independently represents a hydrogen atom or a substituent; R^{77} and R^{78} each independently represents a substituent; and l^{71} and l^{72} each independently represents an integer of from 0 to 4.

9. An iridium complex represented by the following formula (8).

Formula (8)



In the formula (8), R^{81} , R^{82} , R^{83} , R^{84} , R^{85} , and R^{86} each independently represents a hydrogen atom or a substituent; R^{87} and R^{88} each independently represents a substituent; and l^{81} and l^{82} each independently represents an integer of from 0 to 4.

10. The organic electroluminescent element according to the foregoing item 1, wherein at least one of Y^{11} 's is an arylene connecting group, a hetero-arylene connecting group, an alkylene connecting group, or an alkenylene group.

11. The organic electroluminescent element according to the foregoing item 1, having a bond between Y^{11} and Q^{11} to form a condensed ring structure.

12. The organic electroluminescent element according to any one of the foregoing items 1, 2, 10 and 11, wherein Q^{11} and Q^{21} each represents a nitrogen-containing condensed aromatic ring group having three or more rings.

13. The organic electroluminescent element according to any one of the foregoing items 1, 2, 10, 11 and 12, wherein n^{11} is 0.

14. The organic electroluminescent element according to any one of the foregoing items 1 to 5 and 10 to 13, wherein the bonds between $M-L^{11}$, $M-L^{21}$, $M-L^{31}$, $M-L^{41}$ and $M-L^{51}$ are each constituted of only nitrogen-metal bond, oxygen-metal coordinate bond, or sulfur-metal coordinate bond.

15. The organic electroluminescent element according to any one of the foregoing items 1 to 14, wherein the light emitting layer contains at least two kinds of host materials and at least one kind of the compound represented by the general formula (1).

16. The organic electroluminescent element according to the foregoing item 15, containing at least one hole transporting host material and at least one electron transporting host material.

17. The organic electroluminescent element according to the foregoing item 16, wherein the hole transporting host material is an amine derivative.

18. The organic electroluminescent element according to the foregoing item 17, wherein the electron transporting host material is a metal complex.

DETAILED DESCRIPTION OF THE INVENTION

[0009] The formula (I) will be described below.

[0010] Q¹¹ represents a group of forming a nitrogen-containing condensed aromatic ring. The number of nitrogen atoms contained in the nitrogen-containing condensed aromatic ring is preferably from 1 to 3, more preferably 1 or 2, and further preferably 1. The nitrogen-containing condensed aromatic ring may contain an oxygen atom and a sulfur atom other than a nitrogen atom or atoms and carbon atoms.

[0011] The number of condensed rings of the nitrogen-containing condensed aromatic ring is not particularly limited but is preferably from 2 to 5, more preferably from 2 to 4, further preferably from 2 to 3, and particularly preferably 2.

[0012] As nitrogen-containing aromatic rings of forming a nitrogen-containing condensed aromatic ring are preferable 5-membered rings (such as pyrrole, pyrazole, imidazole, thiazole, and oxazole) and 6-membered rings (such as pyridine, pyrazine, and pyrimidine), with 6-membered rings being more preferred.

[0013] Examples of nitrogen-containing condensed aromatic rings include condensed ring bodies of pyrrole, pyrazole, imidazole, thiazole, oxazole, pyridine, pyrazine, and pyrimidine (such as condensed ring bodies with benzene, naphthalene, anthracene, pyrene, perylene, triphenylene, pyridine, pyrazine, pyrimidine, quinoline, quinoxaline, thiophene, furan, etc.). As the nitrogen-containing condensed aromatic ring are preferable quinoline, isoquinoline, quinoxaline, and benzoxazoles (such as benzoimidazole, benzoxazole, and benzothiazole), more preferable quinoline and isoquinoline, and further preferable isoquinoline.

[0014] Q¹¹ may have a substituent. Examples of substituents on Q¹¹ include alkyl groups (preferably ones having from 1 to 30 carbon atoms, more preferably ones having from 1 to 20 carbon atoms, and particularly preferably ones having from 1 to 10 carbon atoms, such as methyl, ethyl, isopropyl, tert-butyl, n-octyl, n-decyl, n-hexadecyl, cyclopropyl, cyclopentyl, and cyclohexyl), alkenyl groups (preferably ones having from 2 to 30 carbon atoms, more preferably ones having from 2 to 20 carbon atoms, and particularly preferably ones having from 2 to 10 carbon atoms, such as vinyl, allyl, 2-butenyl, and 3-pentenyl), alkynyl groups (preferably ones having from 2 to 30 carbon atoms, more preferably ones having from 2 to 20 carbon atoms, and particularly preferably ones having from 2 to 10 carbon atoms, such as propargyl and 3-pentynyl), aryl groups (preferably ones having from 6 to 30 carbon atoms, more preferably ones having from 6 to 20 carbon atoms, and particularly preferably ones having from 6 to 12 carbon atoms, such as phenyl, p-methylphenyl, naphthyl, and anthranyl), amino groups (preferably ones having from 0 to 30 carbon atoms, more preferably ones having from 0 to 20 carbon atoms, and particularly preferably ones having from 0 to 10 carbon atoms, such as amino, methylamino, dimethylamino, diethylamino, dibenzylamino, diphenylamino, and ditolylamino), alkoxy groups (preferably ones having from 1 to 30 carbon atoms, more preferably ones having from 1 to 20 carbon atoms, and particularly preferably ones having from 1 to 10 carbon atoms, such as methoxy, ethoxy, butoxy, and 2-ethylhexyloxy), aryloxy groups (preferably ones having from 6 to 30 carbon atoms, more preferably ones having from 6 to 20 carbon atoms, and particularly preferably ones having from 6 to 12 carbon atoms, such as phenyloxy, 1-naphthyloxy, and 2-naphthyloxy), heterocyclic oxy groups (preferably ones having from 1 to 30 carbon atoms, more preferably ones having from 1 to 20 carbon atoms, and particularly preferably ones having from 1 to 12 carbon atoms, such as pyridyloxy, pyrazolyloxy, pyrimidyloxy, and quinolyloxy), acyl groups (preferably ones having from 1 to 30 carbon atoms, more preferably ones having from 1 to 20 carbon atoms, and particularly preferably ones having from 1 to 12 carbon atoms, such as acetyl, benzoyl, formyl, and pivaloyl), alkoxycarbonyl groups (preferably ones having from 2 to 30 carbon atoms, more preferably ones having from 2 to 20 carbon atoms, and particularly preferably ones having from 2 to 12 carbon atoms, such as methoxycarbonyl and ethoxycarbonyl), aryloxy carbonyl groups (preferably ones having from 7 to 30 carbon atoms, more preferably ones having from 7 to 20 carbon atoms, and particularly preferably ones having from 7 to 12 carbon atoms, such as phenyloxy carbonyl), sulfonyl groups (preferably ones having from 1 to 30 carbon atoms, more preferably ones having from 1 to 20 carbon atoms, and particularly preferably ones having from 1 to 12 carbon atoms, such as mesyl and tosyl), a hydroxyl group, heterocyclic groups (preferably ones having from 1 to 30 carbon atoms, and more preferably ones having from 1 to 12 carbon atoms; examples of hetero atoms include a nitrogen atom, an oxygen atom, and a sulfur atom; and specific examples of heterocyclic groups include imidazolyl, pyridyl, quinolyl, furyl, thienyl, piperidyl, morpholino, benzoxazolyl, benzimidazolyl, benzthiazolyl, carbazolyl, and azevinyl), silyl groups (preferably ones having from 3 to 40 carbon atoms, more preferably ones having from 3 to 30 carbon atoms, and particularly preferably ones having from 3 to 24 carbon atoms, such as trimethylsilyl and triphenylsilyl), and silyloxy groups (preferably ones having from 3 to 40 carbon atoms, more preferably ones having from 3 to 30 carbon atoms, and particularly preferably ones having from 3 to 24 carbon atoms, such as trimethylsilyloxy and triphenylsilyloxy). These substituents may further be substituted.

[0015] Y¹¹ represents a connecting group. The connecting group is not particularly limited but is preferably an alkylene group, an arylene group, a carbonylene group, an -O- group, or an -NR^a- group (R^a represents a hydrogen atom or a

substituent, and examples of substituents include an alkyl group, an aryl group, and a heterocyclic group), more preferably an alkylene group, a carbonylene group, or an -O- group, and further preferably a carbonylene group. Y^{11} cannot be bonded to Q^{11} to form an 8-hydroxyquinolinol ligand.

[0016] M^{11} represents a transition metal ion. The transition metal ion is not particularly limited but is preferably an iridium ion, a platinum ion, a rhenium ion, or a ruthenium ion, more preferably an iridium ion or a platinum ion, and particularly preferably an iridium ion.

[0017] L^{11} represents a ligand. Examples of ligands include ligands described in H. Yersin, *Photochemistry and Photophysics of Coordination Compounds*, published by Springer-Verlag (1987) and Akio Yamamoto, *Organometallic Chemistry - Principles and Applications*, published by Shokabo Publishing Co., Ltd. (1982); preferably halogen ligands (preferably a chlorine ligand and a fluorine ligand), nitrogen-containing heterocyclic ligands (such as bipyridyl, phenanthroline, phenylpyridine, pyrazolylpyridine, and benzimidazolylpyridine), a diketo ligand, a nitrile ligand, a CO ligand, an isonitrile ligand, phosphorus ligands (such as phosphine derivatives, phosphorous acid ester derivatives, and phosphinine derivatives), and carboxylic acid ligands (such as an acetic acid ligand); and more preferably bidentate nitrogen-containing heterocyclic ligands (such as bipyridyl, phenanthroline, phenylpyridine, pyrazolylpyridine, and benzimidazolylpyridine).

[0018] X^{11} represents a counter ion. The counter ion is not particularly limited but is preferably an alkali metal ion, an alkaline earth metal ion, a halogen ion, a perchlorate ion, a PF_6 ion, an ammonium ion (such as a tetramethylammonium ion), a borate ion, or a phosphonium ion, and more preferably a perchlorate ion or a PF_6 ion.

[0019] n^{11} represents an integer of from 0 to 4, preferably from 0 to 3, and more preferably from 0 to 2.

[0020] m^{11} represents an integer of from 1 to 4, and preferably from 1 to 3.

[0021] q^{11} represents an integer of from 0 to 3, preferably 1 or 2, and more preferably 1.

[0022] r^{11} represents an integer of from 0 to 3, preferably from 0 to 2, more preferably 0 or 1, and further preferably 0.

[0023] The transition metal complex represented by the formula (1) is preferably a transition metal complex represented by the formula (2); more preferably an iridium complex represented by the formula (3), the formula (4), or the formula (5) (above all, the iridium complex represented by the formula (3) or the formula (4) is preferable, and the iridium complex represented by the formula (4) is more preferable); and further preferably an iridium complex represented by the formula (6), the formula (7), or the formula (8) (above all, the iridium complex represented by the formula (6) or the formula (7) is preferable, and the iridium complex represented by the formula (6) is more preferable).

[0024] In the compound represented by the general formula (1), it is preferable that at least one of Y^{11} 's represents an arylene connecting group (such as a phenylene connecting group, a naphthalene connecting group, a phenanthrene connecting group, and a triphenylene connecting group), a hetero-arylene connecting group (such as a pyridine connecting group, a pyrazine connecting group, a pyrimidine connecting group, a pyridazine group, a pyrrole group, a pyrazole group, and an imidazole group), an alkylene connecting group (such as a methylene connecting group and an ethylene connecting group), or an alkenylene connecting group (such as a vinylene connecting group); it is more preferable that at least one of Y^{11} 's represents an arylene connecting group or a hetero-arylene connecting group; and it is further preferable that Y^{11} represents an arylene connecting group. When Y^{11} represents an arylene connecting group, examples of ligands include an o-hydroxyphenyl quinoline ligand and an o-hydroxyphenyl isoquinoline ligand.

[0025] In the compound represented by the general formula (1), it is also preferable that a bond is contained between Y^{11} and Q^{11} to form a condensed ring structure (such as a benzo condensed ring, a pyrido condensed ring, and a pyrrolo condensed ring) (for example, an 8-quinolinecarboxylic acid ligand).

[0026] In the compound represented by the general formula (1) or (2), each Q^{11} and Q^{21} preferably represents a nitrogen-containing condensed aromatic ring group having three or more rings, more preferably a nitrogen-containing condensed aromatic ring group having three or four rings, further preferably an azaphenanthrene ring or an azatriphenylene ring, and especially preferably an azaphenanthrene ring.

[0027] In the compound represented by the general formula (1) or (2), it is more preferable that n^{11} is 0.

[0028] In the compounds represented by the general formulae (1) to (5), the bonds between $M-L^{11}$, $M-L^{21}$, $M-L^{31}$, $M-L^{41}$ and $M-L^{51}$ are each preferably constituted of only nitrogen-metal bond, oxygen-metal coordinate bond, or sulfur-metal coordinate bond, and more preferably constituted of only nitrogen-metal bond or oxygen-metal coordinate bond.

[0029] The formula (2) will be described below. Q^{21} , M^{21} , and L^{21} are synonymous with the foregoing Q^{11} , M^{11} and L^{11} , examples of which are also the same, n^{21} represents an integer of from 0 to 4, preferably from 0 to 3, and more preferably from 0 to 2. m^{21} represents an integer of from 1 to 4, and preferably from 1 to 3.

[0030] The formula (3), the formula (4), and the formula (5) will be described below. R^{31} , R^{32} , R^{33} , R^{34} , R^{35} , R^{36} , R^{41} , R^{42} , R^{43} , R^{44} , R^{45} , R^{46} , R^{51} , R^{52} , R^{53} , R^{54} , R^{55} , and R^{56} each independently represents a hydrogen atom or a substituent, and adjacent groups thereof may be bonded to each other to form a condensed ring structure. As the substituent, are enumerated the groups described above for the substituent on Q^{11} . R^{31} , R^{32} , R^{33} , R^{34} , R^{35} , R^{36} , R^{41} , R^{42} , R^{43} , R^{44} , R^{45} , R^{46} , R^{51} , R^{52} , R^{53} , R^{54} , R^{55} , and R^{56} each preferably represents a hydrogen atom, an alkyl group, an aryl group, or a group to form a condensed structure (such as a benzo condensed ring) together with an adjacent group thereof, and more preferably a hydrogen atom or an alkyl group.

[0031] M^{31} , M^{41} , and M^{51} are synonymous with the foregoing M^{21} , examples of which are also the same.

[0032] L^{31} , L^{41} , and L^{51} are synonymous with the foregoing L^{11} , examples of which are also the same.

[0033] m^{31} , m^{41} , and m^{51} each represents an integer of from 1 to 3, preferably 1 or 2, and more preferably 1. n^{31} , n^{41} , and n^{51} each represents an integer of from 0 to 4, preferably 1 or 2, and more preferably 2.

[0034] The formula (6), the formula (7), and the formula (8) will be described below.

[0035] R^{61} , R^{62} , R^{63} , R^{64} , R^{65} , R^{66} , R^{71} , R^{72} , R^{73} , R^{74} , R^{75} , R^{76} , R^{81} , R^{82} , R^{83} , R^{84} , R^{85} , and R^{86} are synonymous with the foregoing R^{31} , R^{32} , R^{33} , R^{34} , R^{35} , R^{36} , R^{41} , R^{42} , R^{43} , R^{44} , R^{45} , R^{46} , R^{51} , R^{52} , R^{53} , R^{54} , R^{55} , and R^{56} , respectively, examples of which are also the same.

[0036] R^{67} , R^{68} , R^{77} , R^{78} , R^{87} , and R^{88} each independently represents a substituent. As the substituent, are enumerated the groups described above for the substituent on Q^{11} . R^{67} , R^{68} , R^{77} , R^{78} , R^{87} , and R^{88} are each preferably an alkyl group, an aryl group, an alkoxy group, or a halogen atom (preferably a fluorine atom), and more preferably an alkyl group or a fluorine atom.


[0037] t^{61} , t^{62} , t^{71} , t^{72} , t^{81} , and t^{82} each independently represents an integer of from 0 to 4, preferably from 0 to 2, more preferably 0 or 1, and further preferably 0.

[0038] The transition metal complex of the invention may be a low-molecular weight compound or may be an oligomer compound or a polymer compound (the weight average molecular weight (as reduced into polystyrene) is preferably from 1,000 to 500,000, more preferably from 2,000 to 100,000, and more preferably from 3,000 to 100,000). In the case of polymer compounds, the structure represented by the formula (1) may be contained in the polymer main chain or may be contained in the polymer side chains. Further, in the case of polymer compounds, they may be a homopolymer compound or a copolymer. The compound of the invention is preferably a low-molecular weight compound.


[0039] In the invention, the transition metal complex represented by the formula (1) is preferably contained in an amount of from 1 % by weight to 20 % by weight, more preferably from 1 % by weight to 10 % by weight, and further preferably from 3 % by weight to 8 % by weight in the light emitting layer.

[0040] Compound examples of the transition metal complex of the invention will be given below, but it should not be construed that the invention is limited thereto.


(1-1)




(1-6)




(1-2)




(1-7)




(1-3)




(1-8)




(1-4)




(1-9)




(1-5)




(1-10)



(1-11)




(1-16)



(1-12)

5

10




15

(1-13)

20

25




30

(1-14)

35

40




45


(1-15)

50


55




(1-17)




(1-18)




(1-19)




(1-20)




(1-21)




(1-26)




(1-22)




(1-27)




(1-23)




(1-28)



(1-24)




(1-29)



(1-25)


5

10



(1-30)


15




(1-31)

20

25




(1-36)




(1-32)

30

35




(1-37)




(1-33)

45

50




(1-38)




55


(1-34)




(1-39)




(1-35)




(1-40)




(1-41)




(1-46)




(1-42)




(1-47)




(1-43)




(1-48)




(1-44)




(1-49)




(1-45)




(1-50)




(1-51)




(1-56)




(1-52)




(1-57)




(1-53)




(1-58)




(1-54)




(1-59)




(1-55)




(1-60)




(1-61)




(1-66)




(1-62)




(1-67)




(1-63)




(1-68)




(1-64)




(1-69)




(1-65)




(1-70)




(1-71)




(1-76)




(1-72)




(1-77)




(1-73)




(1-78)




(1-74)




(1-79)



(1-75)



(1-80)



[0041] The transition metal complex of the invention can be synthesized by various measures. For example, it can be synthesized from a ligand or a dissociated body thereof and a transition metal compound in the absence or presence of a solvent (such as halogen based solvents, alcohol based solvents, ether based solvents, ester based solvents, ketone based solvents, nitrile based solvents, and water) and in the absence or presence of a base (such as various inorganic or organic bases including sodium methoxide, t-butoxypotassium, triethylamine, and potassium carbonate) at a temperature of not higher than room temperature or upon heating (in addition to the usual heating, a heating measure with microwaves is also effective).

[0042] Next, the light emitting element containing the transition metal complex of the invention will be described. The light emitting element of the invention is not particularly limited with respect to the system, driving method and utilization form so far as it is an element utilizing the transition metal complex of the invention, i.e., the transition metal complex represented by the formula (1). As representative light emitting elements, are enumerated organic EL (electroluminescent) elements.

[0043] In the light emitting element of the invention, it is preferable that the light emitting layer contains at least two kinds of host materials and at least one kind of the compound represented by the general formula (1). The host material as referred to herein means a compound mainly bearing injection and transportation of electric charges.

[0044] In the light emitting element of the invention, it is preferable that the light emitting layer contains at least two kinds of a hole transporting host material and an electron transporting host material. The hole transporting host material referred to herein means a compound mainly bearing injection and transportation of holes in the light emitting layer. The electron transporting host material as referred to herein means a compound mainly bearing injection and transportation of electrons in the light emitting layer.

[0045] The hole transporting host material is preferably an amine derivative (for examples, a triphenylamine derivative and a pyrrole derivative), and more preferably a diamine derivative (for examples, a benzidine derivative).

[0046] The electron transporting host material is preferably a nitrogen-containing hetero ring compound (more preferably, a five- or six-membered nitrogen-containing aromatic ring compound) or a metal complex (more preferably, an aluminum complex or a zinc complex), and it is further more preferable to use complexes having a quinolinol ligand and derivatives thereof.

[0047] In the light emitting element of the invention, it is preferable to use a layer containing a compound having an ionization potential of 5.9 eV or more (more preferably 6.0 eV or more) between a cathode and a light emitting layer. It is more preferable to use a layer containing an electron transporting material (an electron transporting layer) having an ionization potential of 5.9 eV or more.

[0048] The formation method of the organic layer (organic compound layer) of the light emitting element containing the transition metal complex of the invention is not particularly limited but includes resistance heating vapor deposition, electron beam irradiation, sputtering, molecular lamination method, coating methods (such as spray coating, dip coating, impregnation, roll coating, gravure coating, reverse coating, roll brushing, air knife coating, curtain coating, spin coating, flow coating, bar coating, micro gravure coating, air doctor coating, blade coating, squeeze coating, transfer roll coating, kiss coating, cast coating, extrusion coating, wire bar coating, and screen coating), inkjet method, printing method, and transfer method. Above all, resistance heating vapor deposition, coating method, and transfer method are preferable from the standpoints of characteristics and manufacture.

[0049] The light emitting element of the invention is an element forming a light emitting layer or a plurality of organic compound films containing a light emitting layer between a pair of electrodes consisting of an anode and a cathode and may have a positive hole injection layer, a positive hole transporting layer, an electron injection layer, an electron transporting layer, a protective layer, etc. in addition to the light emitting layer. Further, these layers may be each a layer provided with other functions. For the formation of each layer, various materials can be used.

[0050] The anode is to supply positive holes into the positive hole injection layer, the positive hole transporting layer, the light emitting layer, and the like. For the anode, metals, alloys, metal oxides, electroconductive compounds, or mixtures thereof can be used, and materials having a work function of 4 eV or more are preferable. Specific examples

include conductive metal oxides such as tin oxide, zinc oxide, indium oxide, and indium-tin oxide (ITO), metals such as gold, silver, chromium, and nickel, mixtures or laminates of the foregoing metals and conductive metal oxides, inorganic conductive substances such as copper iodide and copper sulfide, organic conductive materials such as polyanilines, polythiophenes, and polypyrroles, and laminates thereof with ITO; and preferably conductive metal oxides. Above all, ITO is particularly preferable from the standpoints of productivity, high conductivity, transparency, etc. The film thickness of the anode can properly be chosen but in general, is preferably in the range of from 10 nm to 5 μm , more preferably from 50 nm to 1 μm , and further preferably from 100 nm to 500 nm.

[0051] As the anode, ones having a layer formed on a soda lime glass, an alkali-free glass, a transparent resin substrate, etc. are in general used. In the case where a glass is used, for making the amount of eluted ions from the glass small, it is preferred to use an alkali-free glass with respect to its material quality. Further, in the case where a soda lime glass is used, it is preferred to use a barrier coat such as silica. The thickness of the substrate is not particularly limited so far as a sufficient mechanical strength can be kept. In the case where a glass is used, the thickness of the substrate is in general 0.2 mm or more, and preferably 0.7 mm or more.

[0052] With respect to the preparation of the anode, various methods are used depending on the material. For example, in the case of ITO, the film is formed by a method including electron beam irradiation, sputtering, resistance heating vapor deposition, chemical reaction methods (such as a sol-gel method), and coating of a dispersion of indium-tin oxide.

[0053] The anode can decrease a driving voltage of the element or enhance a light emission efficiency by washing or other processings. For the example, in the case of ITO, UV-ozone processing, plasma processing, etc. are effective.

[0054] The cathode is to supply electrons into the electron injection layer, the electron transporting layer, the light emitting layer, and the like. The cathode is selected while taking into consideration adhesion to adjacent layers thereto, such as the electron injection layer, the electron transporting layer, and the light emitting layer, ionization potential, stability, etc. As materials of the cathode, can be used metals, alloys, metal halides, metal oxides, electroconductive compounds, and mixtures thereof. Specific examples include alkali metals (such as Li, Na, and K) and fluorides or oxides thereof, alkaline earth metals (such as Mg and Ca) and fluorides or oxides thereof, gold, silver, lead, aluminum, sodium-potassium alloys or mixed metals thereof, lithium-aluminum alloys or mixed metals thereof, magnesium-silver alloys or mixed metals thereof, and rare earth metals such as indium and yttrium. Materials having a work function of not more than 4 eV are preferable, and aluminum, lithium-aluminum alloys or mixed metals thereof, and magnesium-silver alloys or mixed metal thereof are more preferable. The cathode can take not only a single layer structure of the foregoing compounds and mixtures but also a laminated structure containing the foregoing compounds and mixtures. For example, laminated structures of aluminum/lithium fluoride or aluminum/lithium oxide are preferable. The film thickness of the cathode can properly be chosen depending on the material but in general, is preferably in the range of from 10 nm to 5 μm , more preferably from 50 nm to 1 μm , and further preferably from 100 nm to 1 μm .

[0055] For the preparation of the cathode, electron beam irradiation, sputtering, resistance heating vapor deposition, coating method, and transfer can be employed. A metal alone can be vapor deposited, and two or more components can be vapor deposited at the same time. In addition, it is possible to form an alloy electrode by vapor deposition of a plurality of metals at the same time. Also, previously prepared alloys may be subjected to vapor deposition.

[0056] It is preferred that the sheet resistance of the anode and cathode is low. The sheet resistance is preferably not more than several hundred Ω/\square (Ω/square).

[0057] As the light emitting layer, can be employed any materials capable of forming a layer having a function to enable to inject positive holes from the anode or the positive hole injection layer or positive hole transporting layer and to inject electrons from the cathode or the electron injection layer or electron transporting layer during the application of an electric field, a function to move injected charges, or a function to provide a field of recombination of positive holes and electrons to cause light emission. Other examples than the transition metal complex of the invention include benzoxazole, benzimidazole, benzothiazole, styrylbenzene, polyphenyl, diphenylbutadiene, tetraphenylbutadiene, naphthalimide, coumarin, perylene, perinone, oxadiazole, aldazine, piperidine, cyclopentadiene, bisstyrylanthracene, quinacridone, pyrrolopyridine, thiadiazolopyridine, styrylamine, aromatic dimethylidene compounds, various metal complexes represented by metal complexes or rare earth complexes of 8-quinolinol, polymer compounds such as polythiophenes, polyphenylenes, and polyphenylene vinylenes, organosilanes, iridium-triphenylpyridine complexes, transition metal complexes represented by platinum porphyrin complexes, and derivatives thereof. The film thickness of the light emitting layer is not particularly limited but in general, is preferably in the range of from 1 nm to 5 μm , more preferably from 5 nm to 1 μm , and further preferably from 10 nm to 500 nm.

[0058] The formation method of the light emitting layer is not particularly limited, but examples include resistance heating vapor deposition, electron beam irradiation, sputtering, molecular lamination method, coating method, inkjet method, printing method, LB method, and transfer method. Above all, resistance heating vapor deposition and coating method are preferable.

[0059] The light emitting layer may be made of a single compound or a plurality of compounds. Further, the light emitting layer may be a single layer or multiple layers, and the respective layers cause light emission of different colors

and, for example, may emit a white light. In the case of a plurality of light emitting layers, the respective light emitting layers may be made of a single material or a plurality of compounds.

[0060] As the positive hole injection layer and positive hole transporting layer, can be employed materials having any one of a function to inject positive holes from the anode, a function to transport positive holes, or a function to block electrons injected from the cathode. Specific examples include carbazole, triazole, oxazole, oxadiazole, imidazole, polyarylethanes, pyrazoline, pyrazolone, phenylenediamine, arylamines, amino-substituted chalcones, styrylanthracene, fluorenone, hydrazone, stilbene, silazanes, aromatic tertiary amine compounds, styrylamine Compounds, aromatic dimethyldiene based compounds, porphyrin based compounds, polysilane based compounds, poly (N-vinylcarbazole), aniline based copolymers, thiophene oligomers, conductive high-molecular weight oligomers such as polythiophene, organosilanes, carbon films, the compound of the invention, and derivatives thereof. The film thickness of the positive hole injection layer and positive hole transporting layer is not particularly limited but in general, is preferably in the range of from 1 nm to 5 μm , more preferably from 5 nm to 1 μm , and further preferably from 10 nm to 500 nm. The positive hole injection layer and positive hole transporting layer may be of a single layer structure composed of one or two or more of the foregoing materials and may also be of a multilayered structure composed of plural layers of the same composition or different compositions.

[0061] Examples of the formation method of the positive hole injection layer and positive hole transporting layer include vacuum vapor deposition method, LB method, a method of coating a solution or dispersion of the foregoing positive hole injection and transporting material in a solvent, inkjet method, printing method, and transfer method. In the case of the coating method, the positive hole injection and transporting material can be dissolved or dispersed together with a resin component. Examples of resin components include polyvinyl chloride, polycarbonates, polystyrenes, polymethyl methacrylate, polybutyl methacrylate, polyesters, polysulfones, polyphenylene oxide, polybutadiene, poly(N-vinylcarbazole), hydrocarbon resins, ketone resins, phenoxy resins, polyamides, ethyl cellulose, polyvinyl acetate, ABS resins, polyurethanes, melamine resins, unsaturated polyester resins, alkyd resins, epoxy resins, and silicone resins.

[0062] As the electron injection layer and electron transporting layer, can be employed materials having any one of a function to inject electrons from the cathode, a function to transport electrons, or a function to block positive holes injected from the anode. Specific examples include triazole, oxazole, oxadiazole, imidazole, fluorenone, anthraquinodimethane, anthrone, diphenylquinone, thiopyran dioxide, carbodiimide, fluorenylidene methane, distyrylpyrazine, naphthalene, aromatic ring tetracarboxylic anhydrides such as perylene, phthalocyanine, various metal complexes represented by a metal complex of 8-quinolinol and metal complexes comprising metal phthalocyanine, benzoxazole, or benzothiazole as a ligand, organosilanes, and derivatives thereof. The film thickness of the electron injection layer and electron transporting layer is not particularly limited but in general, is preferably in the range of from 1 nm to 5 μm , more preferably from 5 nm to 1 μm , and further preferably from 10 nm to 500 nm. The electron injection layer and electron transporting layer may be of a single layer structure composed of one or two or more of the foregoing materials and may also be of a multilayered structure composed of plural layers of the same composition or different compositions.

[0063] Examples of the formation method of the electron injection layer and electron transporting layer include vacuum vapor deposition method, LB method, a method of coating a solution or dispersion of the foregoing electron injection and transporting material in a solvent, inkjet method, printing method, and transfer method. In the case of the coating method, the electron injection and transporting material can be dissolved or dispersed together with a resin component. As the resin component, can be employed those enumerated above in the case of the positive hole injection layer and positive hole transporting layer.

[0064] As the protective layer, can be employed any materials having a function to suppress entrance of substances of promoting deterioration of the element, such as moisture and oxygen, into the element. Specific examples include metals such as In, Sn, Pb, Au, Cu, Ag, Al, Ti, and Ni, metal oxides such as MgO, SiO, SiO₂, Al₂O₃, GeO, NiO, CaO, BaO, Fe₂O₃, Y₂O₃, and TiO₂, metal fluorides such as MgF₂, LiF, AlF₃, and CaF₂, nitrides such as SiN_x and SiO_xN_y, polyethylene, polypropylene, polymethyl methacrylate, polyimides, polyureas, polytetrafluoroethylene, polychlorotrifluoroethylene, polydichlorodifluoroethylene, a copolymer of chlorotrifluoroethylene and dichlorodifluoroethylene, copolymers obtained by copolymerizing a monomer mixture containing tetrafluoroethylene and at least one comonomer, fluorine-containing copolymers having a cyclic structure in the copolymer main chain, water-absorbing substances having a percentage of water absorption of 1 % or more, and moistureproof substances having a percentage of water absorption of not higher than 0.1 %.

[0065] The formation method of the protective layer is not particularly limited, but examples include vacuum vapor deposition method, sputtering method, reactive sputtering method, MBE (molecular beam epitaxy) method, cluster ion beam method, ion plating method, plasma polymerization method (high-frequency excitation ion plating method), plasma CVD method, laser CVD method, hot CDV method, gas source CVD method, coating method, printing method, and transfer method.


EXAMPLES

[0066] The invention will be specifically described below with reference to the following Examples, but it should not be construed that the invention is limited thereto.

(Synthesis of Illustrative Compound (1-3))

[0067] 0.11 g of the following Compound a and 0.3 g of the following Compound b were dissolved in 30 mL of chloroform, to which was then added 0.03 mL of a methanol solution (28 % by weight) of sodium methoxide, and the mixture was stirred under reflux for 6 hours. Water was added to the reaction mixture, and after liquid separation, an organic layer was concentrated. The resulting organic layer was purified by silica gel chromatography (solvent: ethyl acetate) to obtain 0.2 g of Illustrative Compound (1-3). This compound was irradiated with a UV light to obtain brown light emission. Luminescent spectrum (solvent: dichloromethane, 1×10^{-5} moles/L, measured at 20 °C): 636 nm.

[0068] Compounds (1-1) and (1-2) can be synthesized in the same manner as in the foregoing Compound (1-3) while changing the ligand. Luminescent spectrum (solvent: chloromethane) of Compound (1-1): 620 nm, luminescent spectrum (solvent: chloromethane) of Compound (1-2): 503 nm.




(Comparative Example 1)


[0069] A washed ITO substrate was placed in a vapor deposition unit and vapor deposited with TPD (N,N'-diphenyl-N, N'-di-(m-tolyl)-benzidine) in a thickness of 50 nm. The following Compound A and Compound C were then vapor deposited thereon together in a ratio of 1:17 (weight ratio) in a thickness of 36 nm, and the following Azole Compound B was further vapor deposited thereon in a thickness of 36 nm. A patterned mask (a mask having a light emitting area of 4 mm x 5 mm) was placed on the organic thin film, on which were then vapor deposited successively with lithium fluoride in a thickness of 3 nm and aluminum in a thickness of 60 nm, to prepare an element. Using a source measure unit, Model 2400 manufactured by Toyo Corporation, a DC regulated voltage was applied to the EL element to cause light emission, a luminance of which was then measured using a luminance meter, BM-8 manufactured by Topcon Corporation. As a result, green light emission with a maximum luminance of 8,000 cd/m² was obtained.

(Comparative Example 2)


[0070] An element was prepared and evaluated in the same manner as in Comparative Example 1, except for using the following Compound E in place of the Compound A. Only feeble light emission was obtained from the element.




A




B




C



D




E



F



G



H

(Example 1)

[0071] An element was prepared and evaluated in the same manner as in Comparative Example 1, except for using Illustrative Compound (1-3) of the invention in place of the Compound A. As a result, brown light emission with a maximum luminance of 17,000 cd/m² was obtained. A lowest drive voltage (a lowest voltage at which light emission can be visually confirmed) of the element was lowered by 1 V as compared with that of the element of Comparative

Example 1.

(Example 2)

5 **[0072]** A washed ITO substrate was placed in a vapor deposition unit and vapor deposited with TPD (N,N'-diphenyl-N, N'-di-(m-tolyl)-benzidine) in a thickness of 50 nm. The Illustrative Compound (1-3) of the invention and the foregoing Compound C were then vapor deposited thereon together in a ratio of 1:17 (weight ratio) in a thickness of 12 nm. The foregoing Compound D and Compound F were vapor deposited thereon together in a ratio of 1:17 (weight ratio) in a thickness of 24 nm, and the foregoing Azole Compound G was further vapor deposited thereon in a thickness of 36
10 nm. An element was prepared by cathodic vapor deposition and evaluated in the same manner as in Comparative Example 1. As a result, white light emission with a maximum luminance of 13,000 cd/m² was obtained.

(Example 3)

15 **[0073]** 40 mg of polyvinylcarbazole and 12 mg of 2-(4-t-butylphenyl)-5-(p-biphenyl)-1,3,4-oxazdiazole were dissolved in 2.5 mL of dichloroethane, and the solution was spin coated on a washed substrate (at 2,000 rpm for 20 seconds). An organic layer had a film thickness of about 100 nm. An element was prepared by cathodic vapor deposition and evaluated in the same manner as in Comparative Example 1. As a result, brown light emission with a maximum luminance of 8,000 cd/m² was obtained.
20

(Example 4)

[0074] An element was prepared and evaluated in the same manner as in Comparative Example 1, except for using Illustrative Compound (1-1) of the invention in place of the Compound A. As a result, brown light emission with a maximum luminance of 12,000 cd/m² was obtained. A lowest drive voltage (a lowest voltage at which light emission can be visually confirmed) of the element was lowered by 1 V as compared with that of the element of Comparative Example 1.
25

(Example 5)

30 **[0075]** An element was prepared and evaluated in the same manner as in Comparative Example 1, except for using Illustrative Compound (1-2) of the invention in place of the Compound A. As a result, green light emission with a maximum luminance of 27,000 cd/m² was obtained.

35 (Example 6)

[0076] An element was prepared and evaluated in the same manner as in Comparative Example 1, except for using Illustrative Compound (1-64) of the invention in place of the Compound A. As a result, brown light emission of (x, y) = (0.56, 0.43) was obtained, and light emission with a maximum luminance of 16,700 cd/m² was obtained. An external quantum efficiency was 9.6 %.
40

(Example 7)

45 **[0077]** An element was prepared and evaluated in the same manner as in Comparative Example 1, except for using Illustrative Compound (1-68) of the invention in place of the Compound A. As a result, high-luminance light emission exceeding 1,000 cd/m² was obtained.

(Example 8)

50 **[0078]** An element was prepared and evaluated in the same manner as in Comparative Example 1, except for using Illustrative Compound (1-75) of the invention in place of the Compound A. As a result, high-luminance light emission exceeding 1,000 cd/m² was obtained.

(Example 9)

55 **[0079]** An element was prepared and evaluated in the same manner as in Example 1, except for using a mixture (1:1) of TPD and Compound H in place of the Compound A. As a result, driving durability at an initial luminance of 200 cd/m² was enhanced by two times as compared with the element of Example 1.

[0080] High-luminance light emitting elements capable of emitting a light to multiple colors can be prepared in the same manner even using other compounds of the invention.

[0081] The light emitting element of the invention using the compound of the invention is able to undergo light emission with a high luminance and emits a light to multiple colors (especially brown to red colors). Accordingly, the light emitting element of the invention can suitably be used in optical fields such as display elements, displays, backlights, electrophotography, illumination light sources, recording light sources, exposure light sources, read out light sources, signals, signboards, interiors, and optical communications.

[0082] Further, the compounds of the invention can be applied to medical utilizations, fluorescent brighteners, photographic materials, UV absorbing materials, laser pigments, color filter dyes, color conversion filters, and the like.

[0083] This application is based on Japanese Patent application JP 2003-298978, filed August 22, 2003, the entire content of which is hereby incorporated by reference, the same as if set forth at length.


Claims

1. An organic electroluminescent element comprising:

a pair of electrodes; and

at least one organic layer provided between the pair of electrodes, at least one of the at least one organic layer being a light emitting layer,


wherein the light emitting layer comprises at least one transition metal complex represented by the formula (1):



wherein Q¹¹ represents a group for forming a nitrogen-containing condensed aromatic ring, Y¹¹ represents a connecting group; M¹¹ represents a transition metal ion; L¹¹ represents a ligand; X¹¹ represents a counter ion; Y¹¹ is not bonded to Q¹¹ to form an 8-hydroxyquinolinol ligand; n¹¹ represents an integer of from 0 to 4; m¹¹ represents an integer of from 1 to 4; q¹¹ represents an integer of from 0 to 3; and r¹¹ represents an integer of from 0 to 3.

2. The organic electroluminescent element of claim 1, wherein the transition metal complex represented by the formula (1) is a transition metal complex represented by the


formula (2):



wherein Q²¹ represents a group for forming a nitrogen-containing condensed aromatic ring; M²¹ represents a transition metal ion; L²¹ represents a ligand; n²¹ represents an integer of from 0 to 4; and m²¹ represents an integer of from 1 to 4.


3. The organic electroluminescent element of claim 2, wherein the transition metal complex represented by the for-

mula (2) is represented by the formula (3):




15 wherein M^{31} represents a transition metal ion; R^{31} , R^{32} , R^{33} , R^{34} , R^{35} , and R^{36} each independently represents a hydrogen atom or a substituent, and adjacent groups thereof may be bonded to each other to form a condensed ring structure; L^{31} represents a ligand; n^{31} represents an integer of from 0 to 4; and m^{31} represents an integer of from 1 to 3.

- 20 4. The organic electroluminescent element of claim 2, wherein the transition metal complex represented by the formula (2) is represented by the formula (4):



35 wherein M^{41} represents a transition metal ion; R^{41} , R^{42} , R^{43} , R^{44} , R^{45} , and R^{46} each independently represents a hydrogen atom or a substituent, and adjacent groups thereof may be bonded to each other to form a condensed ring structure; L^{41} represents a ligand; m^{41} represents an integer of from 1 to 3; and n^{41} represents an integer of from 0 to 4.


- 40 5. The organic electroluminescent element of claim 2, wherein the transition metal complex represented by the formula (2) is represented by the formula (5):



55 wherein M^{51} represents a transition metal ion; R^{51} , R^{52} , R^{53} , R^{54} , R^{55} , and R^{56} each independently represents a hydrogen atom or a substituent, and adjacent groups thereof may be bonded to each other to form a condensed ring structure; L^{51} represents a ligand; m^{51} represents an integer of from 1 to 3; and n^{51} represents an integer of


from 0 to 4.

6. An iridium complex represented by the formula (A):




wherein A¹, A², A³, and A⁴ each independently represents a hydrogen atom or a substituent, and adjacent groups thereof may be bonded to each other to form a benzene ring; A⁵ and A⁶ each independently represents a substituent; and t⁶¹ and t⁶² each independently represents an integer of from 0 to 4.

7. The iridium complex of claim 6, wherein the formula (A) is represented by the formula (6):



wherein R⁶¹, R⁶², R⁶³, R⁶⁴, R⁶⁵, and R⁶⁶ each independently represents a hydrogen atom or a substituent; R⁶⁷ and R⁶⁸ each independently represents a substituent; and t⁶¹ and t⁶² each independently represents an integer of from 0 to 4.


8. The iridium complex of claim 6, wherein the formula (A) is represented by the formula (7):



wherein R⁷¹, R⁷², R⁷³, R⁷⁴, R⁷⁵, and R⁷⁶ each independently represents a hydrogen atom or a substituent; R⁷⁷

and R^{78} each independently represents a substituent; and t^{71} and t^{72} each independently represents an integer of from 0 to 4.

9. The iridium complex of claim 6, wherein the formula (A) is represented by the formula (8):



wherein R^{81} , R^{82} , R^{83} , R^{84} , R^{85} , and R^{86} each independently represents a hydrogen atom or a substituent; R^{87} and R^{88} each independently represents a substituent; and t^{81} and t^{82} each independently represents an integer of from 0 to 4.

10. The organic electroluminescent element of claim 1, wherein at least one of $Y^{11s'}$ is an arylene connecting group, a hetero-arylene connecting group, an alkylene connecting group, or an alkenylene group.



European Patent
Office

PARTIAL EUROPEAN SEARCH REPORT

Application Number

which under Rule 45 of the European Patent Convention EP 03 01 9525
shall be considered, for the purposes of subsequent
proceedings, as the European search report

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
P,X	WO 03 001616 A (TAKEUCHI MASATAKA ;ITO NAOKO (JP); NAIJO SHUICHI (JP); KAMACHI MOT) 3 January 2003 (2003-01-03) page 51 Formula E-1 ---	6-10	C09K11/06 H05B33/14 H01L51/30
X	WO 02 064700 A (MATSUSUE NORIYUKI ;SANYO ELECTRIC CO (JP); HAMADA YUJI (JP)) 22 August 2002 (2002-08-22) page 31 Formula C3 ---	6-10	
X	WO 01 41512 A (UNIV PRINCETON ;UNIV SOUTHERN CALIFORNIA (US)) 7 June 2001 (2001-06-07) * figures 1,2,39 *	6-10	
X	KAWAMURA ET. AL.: J. APP. PHYSICS, vol. 92, no. 1, 1 June 2002 (2002-06-01), pages 87-93, XP002265062 * figure 1 * -----	6-10	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C09K H05B H01L
INCOMPLETE SEARCH			
<p>The Search Division considers that the present application, or one or more of its claims, does/do not comply with the EPC to such an extent that a meaningful search into the state of the art cannot be carried out, or can only be carried out partially, for these claims.</p> <p>Claims searched completely :</p> <p>Claims searched incompletely :</p> <p>Claims not searched :</p> <p>Reason for the limitation of the search: see sheet C</p>			
Place of search		Date of completion of the search	Examiner
MUNICH		15 December 2003	Saldamli, S
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 02 (P) 4007



European Patent
Office

INCOMPLETE SEARCH
SHEET C

Application Number
EP 03 01 9525

Claim(s) searched completely:
6-10

Claim(s) not searched:
1-5

Reason for the limitation of the search:

Present claim 1 relates to an extremely large number of possible compounds. In fact, the claim contains so many options that a lack of clarity and conciseness within the meaning of Article 84 EPC arises to such an extent as to render a meaningful search of the claim impossible. Consequently, the search has been carried out for those parts of the application which do appear to be clear and concise, namely the technical feature represented by the markush formula A of claim 6.

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 03 01 9525

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

15-12-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 03001616 A	03-01-2003	JP 2003119179 A	23-04-2003
		JP 2003113246 A	18-04-2003
		JP 2003147021 A	21-05-2003
		JP 2003171391 A	20-06-2003
		JP 2003077675 A	14-03-2003
		JP 2003073666 A	12-03-2003
		WO 03001616 A2	03-01-2003
		JP 2003206320 A	22-07-2003
WO 02064700 A	22-08-2002	WO 02064700 A1	22-08-2002
WO 0141512 A	07-06-2001	AU 1807201 A	12-06-2001
		CN 1413426 T	23-04-2003
		EP 1252803 A1	30-10-2002
		JP 2003515897 T	07-05-2003
		WO 0141512 A1	07-06-2001
		US 2003017361 A1	23-01-2003
		US 2002034656 A1	21-03-2002

EPO FORM P/458

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)